

Tepco technical products

Division of Development Associates, Inc. 300 Old Baptist Rd. N. Kingstown, RI 02852
Tel 401-884-3057 Fax 401-885-7888 website: www.tepco-usa.com

Page 1 of 1

Product Name T-16A
Ref No: T16ADSV4.doc

Revision Date: 5/30/2002
Supersedes: 12/6/2001

Technical Data Sheet **T-16A Ribbon Cable Cement**

Wgt. Per Gal 7.5 lbs.

The **T-16A Ribbon Cable Cement** has been specifically formulated for bonding individual vinyl insulated wires together for manufacturing flat multi-colored ribbon cables.

The cement is applied to the wires by pulling the insulated conductors through a reservoir containing the cement. The excess cement is removed from the wires by means of felt wiping pads located on the reservoir. After application, the T-16A cement should be dried in an oven using moderate forced hot air before it is wound on wheels.

When completely dry, the T-16A cement will produce an excellent bond between the insulated wires, maintaining flexibility and toughness, together with the proper degree of stripability. The dry film will not support combustion upon removal of the flame.

T-16A Ribbon Cable Cement may be thinned if necessary by using the **T-17A Ribbon Cable Cement Thinner**.

All information, recommendations and suggestions contained herein are to the best of our knowledge true and accurate, but are made without guarantee. No warranty of fitness for a particular purpose is made. Nothing herein shall be construed to allow infringement of any patent.