

# Tepco technical products

Division of Development Associates, Inc. 300 Old Baptist Rd. N. Kingstown, RI 02852  
Tel 401-884-3057 Fax 401-885-7888 website: www.tepco-usa.com

Page 1 of 1

Product Name T-301A  
Ref No: T301ADSV3.doc

Revision Date: 12/6/2001  
Supersedes: 10/2/01

## Technical Data Sheet **T-301A Urethane Cable Coating**

### Description:

**T-301A Urethane Cable Coating** is a clear, non-yellowing, elastomeric polyurethane solution. It is designed for application over braided cable insulation. It dries to a tough flexible film by solvent evaporation. Speed of drying time can be increased by forced hot air drying. The T-301A offers good abrasion, impact and solvent resistance, as well as excellent hydrolytic stability and gloss retention.

### Typical Properties

Percent Solids by Weight:	25+/-2
Viscosity:	Brookfield, #4 sp @ 10 rpm, 23°C 10,000-15,000
Weight per Gallon:	7.5 Pounds
Specific Gravity:	0.9 @25°C
Color:	Clear
Dry Time:	Wet Film on Glass 77°F 5 Minutes 150°F 1.5 Minutes

### Recommended Storage

To insure a longer shelf life, store in a cool, dry place. At least below 80°F

All information, recommendations and suggestions contained herein are to the best of our knowledge true and accurate, but are made without guarantee. No warranty of fitness for a particular purpose is made. Nothing herein shall be construed to allow infringement of any patent.