

Product Name T-51A
Ref No: T51ADSV1.doc

Revision Date: 5/30/2002

Technical Data Sheet **T-51A Ribbon Cable Cement**

Wgt. Per Gal 7.25 lbs.

The **T-51A Ribbon Cable Cement** contains a stronger solvent system than T-16A, for use with harder to bond vinyl insulations.

The cement is applied to the wires by pulling the insulated conductors through a reservoir containing the cement. The excess cement is removed from the wires by means of felt wiping pads located on the reservoir. After application, the T-51A cement should be dried in an oven using moderate forced hot air before it is wound on wheels.

When completely dry, the T-51A cement will produce an excellent bond between the insulated wires, maintaining flexibility and toughness, together with the proper degree of stripability. The dry film will not support combustion upon removal of the flame.

T-51A Ribbon Cable Cement may be thinned if necessary by using the **T-17A Ribbon Cable Cement Thinner**.